

## FLAMMABILITY TEST REPORT

**Report No.:** LEHTX00763228    **Date Received:** 11/08/14    **Date Tested:** 15/08/14    **Date Issued:** 15/08/14

**Company Name & Address:** VITAFOAM MAGYARORSZÁG KFT  
VITAFOAM HUNGARY LTD  
VITA COMFORT FOAMS DIVISON OF BRITISH VITA UNLIMITED  
REGISTERED OFFICE  
SZÉKHELY: H-7030 PAKS  
HRSZ 8806/2

**Contact Name:** SORIN VANGHELE

### Sample Details

Order No.: Not stated  
Style No.: Not stated  
Batch No.: P 193  
Quality: CH 4560  
Colour: Blue  
Supplier: Not stated  
End Use: Not stated  
Quoted Fibre Composition: Not stated  
Retailer: Not stated  
Sample Description: Blue coloured polyurethane foam

Test Method	Pre Treatment	Flammability Performance Requirements	Result
BS 5852: Part 2: 1982, Ignition source 5 (Crib 5) as modified by Schedule 1 Part 1 of the Furniture & Furnishings (Fire) (Safety) Regulations 1988 (As Amended).	None	As Schedule 1 Part 1 (Ignition test for polyurethane foam in slab or cushion form) of The Furniture and Furnishings (fire) (safety) Regulations 1988 (as amended).	<b>Complies</b>

.....  
**STEVEN OWEN**  
(Chemical Technologist)

  
.....  
**ANDREW HALLETT**  
(Flammability Technician)

.....  
**CAROLE SPOWART**  
(Flammability Technician)

.....  
**SIMON CHEE**  
(Operations Manager)

Report No.: LEHTX00763228 Page 1 of 2

## FLAMMABILITY TEST REPORT

### Filling Specification

Filling Type: Polyurethane foam  
Density / Hardness: Not stated / Not stated  
Cover Fabric: Standard test fabric as detailed in Schedule 1 Part 1 of The Furniture (Fire) (Safety) Regulations 1988 (as amended).

### Conditioning

Prior to Testing: At least 72 hours in ambient indoor conditions, then at least 16 hours in an atmosphere having a temperature of 20±5°C and a relative humidity of 50±20%  
At Time of Testing: Temperature between 15°C & 30°C. Relative humidity between 20% & 70%

### Test Results

*"The following test results relate only to the ignitability of the combination of upholstery composites under the particular conditions of test; they are not intended as a means of assessing the fully potential fire hazard of the materials in use."*

Pass / Fail Criteria	Initial test	Repeat test
<b>Progressive smouldering failure</b>		
Externally detectable amounts of smoke, heat or glowing 60 min after crib ignition	No	No
Escalating smouldering behaviour rendered the test unsafe to continue and required forcible extinction	No	No
Smouldering essentially consumed the test specimen within the duration of the test	No	No
<b>Flaming failure</b>		
The test specimen continued to flame for more than 10 minutes after the ignition of the crib	No	No
Escalating combustion behaviour rendered the test unsafe to continue and required forcible extinction	No	No
Flaming essentially consumed the test specimen within the duration of the test	No	No
<b>Final examination</b>		
Progressive smouldering was observed when the sample was dismantled	No	No
<b>Comments</b>		
Time to extinction of flames after crib ignition	3 Minutes 27 Seconds	6 Minutes 00 Seconds
Time to extinction of glowing after crib ignition	Due to the position of the crib within the test specimen it was not possible to see when glowing ceased	Due to the position of the crib within the test specimen it was not possible to see when glowing ceased
Time to extinction of smoke after crib ignition	Due to the amount of smoke in the test enclosure it was not possible to see when smoking ceased	Due to the amount of smoke in the test enclosure it was not possible to see when smoking ceased
Maximum extent of damage to back (mm) Length / Width	400      114	400      108
Maximum extent of damage to base (mm) Length / Width	90              122	94              140
The resultant mass loss exceeded 60g	No (25g)	No (42g)
<b>Test Result</b>	<b>PASS</b>	<b>PASS</b>

### Conclusions

The sample tested meets the requirements of Schedule 1 Part 1 (Ignition test for polyurethane foam in slab or cushion form) of The Furniture and Furnishings (fire) (safety) Regulations 1988 (as amended). **PASS.**

This report is made solely on the basis of your instructions and/or information and materials supplied by you. It is not intended to be a recommendation for any particular course of action. Intertek does not accept a duty of care or any other responsibility to any person other than the Client in respect of this report and only accepts liability to the Client insofar as is expressly contained in the terms and conditions governing Intertek's provision of services to you. Intertek makes no warranties or representations either express or implied with respect to this report save as provided for in those terms and conditions. We have aimed to conduct the Review on a diligent and careful basis and we do not accept any liability to you for any loss arising out of or in connection with this report, in contract, tort, by statute or otherwise, except in the event of our gross negligence or willful misconduct.