



### SPECIFICATIE TEHNICA TECHNICAL DATA SHEET

<b>Tip spuma Foam grade</b>	<b>CM 3538</b>
---------------------------------	----------------

<b>Caracteristici Characteristics</b>	<b>Standard Norm</b>	<b>Unitate de masura Measure</b>	<b>Valoare Value</b>
<b>Densitate Density</b>	ISO 845 : 1988	Kg/m <sup>3</sup>	<b>33 - 36</b>
<b>Duritate Hardness – CLD 40%</b>	ISO 3386/1: 1986	kPa	<b>3.5 – 4.5</b>
<b>Rezistenta la tractiune, min. Tensile strength, min.</b>	ISO 1798: 1997	kPa	<b>70</b>
<b>Alungire la rupere, min. Elongation at break, min.</b>	ISO 1798: 1997	%	<b>140</b>
<b>Deformarea remanenta, max Compression Set, max</b>	ISO 1856:2000	%	<b>7</b>
<b>Standard de ignifugare Fire retardant standard</b>	English Standard BS5852 Max. 0.060 kg		
<b>Culoare Color</b>	<b>Alb White</b>		

NOTA : Culoarea spumei poliuretanic se realizeaza in functie de cerintele clientului.  
NOTE: The foam colour can be produce as the clients require.