



Vitafoam Magyarország Kft. / Vitafoam Hungary Ltd.
Vita Comfort Foams division of The Vita Group
Registered office / Székhely: H-7030 Paks, Hrsz: 8806/2 (Ipari Park)
Registered No. / Cg. 17-09-006137
Tel.: 00 36 75 519 701
Fax: 00 36 75 519 a
e-mail: laboratory@vitahungary.hu

VASCO POLIURETÁN HAB
VASCO POLYURETHANE FOAM GRADE
SPUME VASCOELASTICE
VASCO SCHAUMEN

Fizikai tulajdonságok		Alkalmazott szabvány
Foam properties Proprietati fizice Physische eigenschaft	VA4015	Test method Metoda de testare Test Prozedur
Piece Density [kg/m³] <i>Nettó Testsűrűség [kg/m³]</i> <i>Densitate Neta [kg/m³]</i> <i>Netto R.G. [kg/m³]</i>	35 - 45	ISO 845 : 1988
Keményiség / Hardness / Resistenta la comprimare / Härte CLD, 40 % [kPa]	1,0 - 2,0	ISO 3386/1 : 1986
Szakítószilárdság, minimum [kPa] <i>Tensile strength, minimum [kPa]</i> <i>Rezistenta la Rupere [kPa]</i> <i>Zugfestigkeit, minimum [kPa]</i>	40	ISO 1798 : 1997
Szakadási nyúlás, minimum [%] <i>Elongation at break, minimum [%]</i> <i>Alungirea la rupere, minim [%]</i> <i>Dehnung beim Bruch, minimum [%]</i>	150	ISO 1798 : 1997
Maradandó összenyomódás, maximum [%] <i>Compression set, maximum [%]</i> <i>Deformarea remanenta [%]</i> <i>Druckverformungsreset, maximum [%]</i>	10	ISO 1856 : 2000
Memory effect (sec)	5	Vita test
Standard szín <i>Standard colour</i> <i>Culoare</i> <i>Farben</i>	zöld <i>green</i> <i>verde</i> <i>grün</i>	